

# Bekaert Steel Fibres: product data sheet **LH 35/0.7**

## DESCRIPTION

Bekaert steel fibres are filaments of wire, deformed and cut to lengths for reinforcement of concrete




## GEOMETRY


Product	LH 35 / 0.7	
Loose (L) Glued (G)	L	
Hooked (H) Undulated (U)	H	<b>TOLERANCES ON AVERAGE VALUE</b>
Length L <sub>nom</sub> (mm)	35	± 5%
Diameter D <sub>nom</sub> (mm)	0.75	± 5%
Aspect ratio L/D	47	± 7.5%
Nominal wire tensile strength (N/mm <sup>2</sup> )	1180	± 7.5%

Values are indicative only. Modifications reserved. All details describe our products in general form only.

## PACKAGING



PALLET: 1200 kg (60x20kg)  
or 1000 kg (50x20kg)



BIGBAG: 800 kg


## APPROVALS

**Minimum dosage:**  
30 kg per m<sup>3</sup>  
(according to EN 14889-1)



CE LABEL: Bekaert Steel Fibres are certified for CE mark system 1: steel fibres for structural use. For detailed info: CE info sheet available on request.

## STORAGE



## DOSING AND MIXING

- A continuous grading is preferred
- A preliminary test is advised
- Mix until all fibres are distributed uniformly

## TRANSPORT OF ALL PRODUCTS

### Truck transport: max. load

- 20 pallets / truck
- 22 big-bags / truck

### Sea transport: containers

- 20 big-bags / 40 ft container
- 20 pallets / 40 ft container
- 20 pallets / 20 ft container

## CUSTOMER SERVICE

NV Bekaert SA [www.bekaert.com/building](http://www.bekaert.com/building)  
[infobuilding@bekaert.com](mailto:infobuilding@bekaert.com)  
 Bekaertstraat 2  
 BE-8550 Zwevegem Belgium  
 T+32 56 76 61 10  
 F+32 56 76 79 47

All Bekaert company names are trademarks owned by NV Bekaert SA Zwevegem - Belgium. Modifications reserved. All details describe our products in general form only. For ordering and design only use official specifications and documents.